

## Technical Data Sheet

**Aggregate Name:** Emerald Silver Sizes Available: 1-3mm, 2-5mm

**Material:** Quartz

Product Description: Dark green aggregate

with silver flecks, angular in shape



## **Technical Information**

Tested in accordance with BS EN 1097-2: 2010 - Annex B LA Abrasion = 20

Tested in accordance with BS EN 1097-6: 2013 - Clause 8

Particle density on an oven-dried basis =  $2.64 \text{ Mg/m}^3$ Particle density on a saturated and surface-dried basis =  $2.71 \text{ Mg/m}^3$ Apparent Particle density = 2.84 Mg/m<sup>3</sup> Water absorption (of dry mass) = 2.70%

> All test results produced in accordance with UKAS standards at an independent UKAS approved laboratory