



Technical Data Sheet

Aggregate Name: Red Granite
Sizes Available: 1-3mm, 2-5mm

Material: Granite

Product Description: Uniform dark red aggregate, angular in shape



Technical Information

Tested in accordance with BS EN 1097-2: 2010 - Annex B
LA Abrasion = 16

Tested in accordance with BS EN 1097-6: 2013 - Clause 8

Particle density on an oven-dried basis = 2.44 Mg/m³

Particle density on a saturated and surface-dried basis = 2.47 Mg/m³

Apparent Particle density = 2.54 Mg/m³

Water absorption (of dry mass) = 1.50%

All test results produced in accordance with UKAS standards at
an independent UKAS approved laboratory